

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 619 343 A1

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **94105321.7**

(51) Int. Cl.⁵: **C08L 51/06, C09D 151/06,
C08K 5/54**

(22) Date of filing: **06.04.94**

(30) Priority: **06.04.93 IT MI930676**

(43) Date of publication of application:
12.10.94 Bulletin 94/41

(84) Designated Contracting States:
BE DE DK FR GB IT NL SE

(71) Applicant: **Himont Incorporated**
2801 Centerville Road
New Castle County Delaware (US)

(72) Inventor: **Marzola, Roberto**
31, Via Mario Azzi
I-44100 Ferrara (IT)
Inventor: **Rigosi, Gian Luigi**
42, Via Pomposa
I-44100 Ferrara (IT)

(74) Representative: **Zumstein, Fritz, Dr. et al**
Dr. F. Zumstein
Dipl.-Ing. F. Klingseisen
Bräuhausstrasse 4
D-80331 München (DE)

(54) **Process for coating metal pipes with polyolefin materials.**

(57) Process for coating metal pipes, where the coating materials used are specific polyolefin compositions partially crosslinked by grafting the polyolefin backbone with an alkenyl-substituted alkoxysilane and then by reacting the grafted polyolefin with water.

EP 0 619 343 A1

The present invention concerns a process for the coating of metal pipes with polyolefin materials.

Metal pipes usually made of steel and coated with plastic materials are widely used for the construction of pipe-lines destined for the conveyance of fluid materials, such as oil, natural gases or water, even for long distances.

Said pipe-lines must be able to withstand the most varied environmental conditions, and in some cases, the high temperatures which are maintained in the vicinity of pumping stations, for example, or may be typical of certain fluids which are extracted directly from the subsoil. Therefore the coatings must be carefully selected in order to obtain high levels of corrosion resistance. Some types of coatings made with polyolefin materials have been found to be particularly suited for this purpose.

Moreover, in order not to create weak points in the line (at the welded points between the pipes, for example) one must be able to repair the damaged or removed portions of the above mentioned coating in such a way as to obtain mechanical properties which are as similar as possible to those of the original coating.

Published European Patent Application n. 444446 teaches that the removed or damaged portions of polyolefin material coatings of metal pipes can be efficiently repaired by using patches or strips of polypropylene materials which are fastened to the pipes by way of specific adhesive polymer compositions. However, the above mentioned polypropylene materials based on polymers which are not crosslinked are not suited for coating large segments of metal pipes, and require accurate application procedures. In particular, given the low viscoelasticity of the above polymers in the molten state, their heating step, which is protracted until the softening or melting point is reached in order to obtain optimal adhesion, must be carried out in such a way as to avoid nonhomogeneity and/or lacerations in the final coating.

For this purpose heat sources are used which allow one to obtain homogeneous heat and avoid the use of flame in direct contact with the polymer, such as, for example, radiant panels, electric heating coils, induction ovens or infra-red lights.

The above mentioned devices, moreover, allow one to obtain good heat diffusion inside the layer of the polyolefin coating. However, said devices are relatively complex and expensive, and are not always readily available at the sites where the pipes are being laid.

This invention provides a new process for coating metal pipes based on the use of certain partially crosslinked olefin polymers which besides giving the coating high mechanical and corrosion resistance characteristics, also have the advantage of being easy to apply to the metal pipes by using extremely simple pre-heating and post-heating devices, such as gas torches. In spite of the fact that said devices produce localized and nonhomogeneous heat, the polymers used in the process of the present invention do not create nonhomogeneity and/or tearing problems, and allow one to obtain a good and homogeneous heat diffusion throughout of the coating layer.

Moreover, given their high viscoelasticity in the molten state, said partially crosslinked olefin polymers can be easily used to coat long sections of metal pipes, since they can withstand considerable mechanical stress, even in the molten state, without tearing.

Therefore, an object of the present invention is a process for coating metal pipes wherein as the coating material is used a polyolefin composition comprising:

A) 10-60, preferably 20-50, parts by weight of homopolymer polypropylene having an isotactic index higher than 90, particularly ranging from 95 and 98, or a crystalline copolymer of propylene with ethylene and/or with a $\text{CH}_2 = \text{CHR}$ α -olefin, where R is an alkyl radical with 2-6 carbon atoms, containing over 85 % by weight, preferably 90 to 99 % by weight, of propylene and having an isotactic index higher than 85 %, preferably higher than 90 %, or mixtures thereof;

B) 10-40 parts by weight of a polymer fraction containing ethylene, which is insoluble in xylene at ambient temperature; preferably 10-40, preferably 10-20 parts by weight of an essentially linear copolymer of ethylene with propylene, which copolymer constitutes a fraction insoluble in xylene at ambient temperature;

C) 30-60, preferably 30-50, parts by weight of an amorphous ethylene-propylene copolymer fraction containing 40-70% by weight, preferably 45 - 60 % by weight, of ethylene and optionally containing minor proportions of a diene, which fraction is soluble in xylene at ambient temperature;

said polyolefin composition being crosslinked by grafting onto the polyolefin backbone an alkenyl-substituted alkoxy silane, and then by reacting with water until one obtains hot-set values, according to the method CEI 20-31, lower than 175%, preferably lower than 120%, at 200 °C, and lower than 15%, preferably lower than 10%, at 23 °C.

The terms "insoluble" in the definition of component B and "soluble" in the definition of component C are preferably to mean "totally insoluble" or "totally soluble", respectively.

Polymer compositions comprising (A) + (B) + (C) are described in published european patent application n. 400333.

Generally, the total content of ethylene polymerized in the above mentioned compositions ranges from 20 to 60% by weight.

5 The $\text{CH}_2 = \text{CHR}$ α -olefin of fraction (A), where R is an alkyl radical with 2-6 carbon atoms, is preferably selected from 1-butene, 1-pentene, and 4-methyl-1-pentene.

The diene of fraction (C) is preferably selected from butadiene, 1,4-hexadiene, 1,5-hexadiene, ethylidene-1-norbornene and may be present in an amount from 1 to 10% by weight, preferably 1 to 5% by weight.

10 The molecular weight of the various fractions (determined by measuring the intrinsic viscosity in tetrahydronaphthalene at 135 °C) varies in function of the nature of the components and the total melt index of the composition, and it is preferably comprised between the following limits:

- 0.5 - 3 dl/g for fraction (A);
- 2 - 8 dl/g for fractions (B) and (C).

15 The electronic microscope examination of the compositions indicates that the dispersed phase is made up of an amorphous ethylene-propylene copolymer, and the average dimensions of its particles is less than 2 μm .

Preferred examples of alkenyl-substituted alkoxysilanes are those of formula $\text{SiR}_n(\text{OR}')_{4-n}$ wherein R is vinyl or allyl, R' is a C_1 - C_8 alkyl radical, n is 1, 2 or 3.

20 Specific examples of alkenyl-substituted alkoxysilanes used to obtained the crosslinking of the above compositions are vinyltriethoxysilane, allyltriethoxysilane and divinyltriethoxysilane.

Generally, the alkenyl-substituted alkoxysilanes are grafted onto polyolefin backbone through the alkenyl moiety by extrusion in the presence of peroxides, such as dicumylperoxide, tert-butyl peroxy-pivalate and 2,5-dimethyl-2,5-di(tert-butylperoxy)hexane. Extruders which are well known in the art are used for this purpose at temperatures ranging from 180 to 230 °C.

25 The quantity of alkenyl-substituted alkoxysilane used generally ranges from 1% to 3% by weight with respect to the polyolefin composition; the quantity of peroxide used generally ranges from 0.05% to 0.2% by weight with respect to the polyolefin composition.

The polymer material thus obtained is then contacted with water, by exposing it to steam or moisture in the air, for example, or by immersing it in water at ambient temperature or higher, in order to obtain crosslinking. To promote said crosslinking it is preferred if prior to the water treatment the polymer composition grafted with the silane is subjected to an additional extrusion step where a crosslinking catalyst is added. The conditions and apparatuses used in said extrusion phase are the same that are used for the grafting with the silane. Preferred examples of cross-linking catalysts are tin dioctate and tin dibutyl dilaurate; generally the cross-linking catalysts are added in quantities ranging from 0.15 to 0.3% with respect to the polymer.

The reaction with water can also occur after the grafted polymer composition has been converted into films, tapes or strips to be used in the process of the present invention, which will be described in more detail later on.

40 The hot-set test according to CEI (COMITATO ELETTROTECNICO ITALIANO) 20-31 allows one to verify that the crosslinking has reached the desired levels for use in the process of the present invention. The CEI 20-31 method is described in the first issue of CEI methods, volume 605, February 1983. The hot-set values at 200 °C are obtained by subjecting the specimens to a load of 0.2 MPa for 15 minutes at the above mentioned temperature, and measuring the percentage elongation of the specimens. The values at 23 °C are obtained by maintaining the same specimens at 200 °C for 5 minutes without load, and then cooling them to 23 °C. Thus one obtains an evaluation of the capability of the crosslinked polyolefin composition to withstand mechanical stress in the molten state, and of its elastic recovery after stress release and cooling.

50 The crosslinked polyolefin composition can be applied on the metal pipe directly or by using hot-melt adhesives. In the case of direct application, the crosslinked polyolefin composition is mixed, either before or after the crosslinking step, with a polypropylene which is modified with maleic anhydride, isophorone bismaleamic acid or acrylic acid in quantities ranging from 1% to 10% by weight. The quantity of modified polypropylene which is added to the crosslinked polyolefin composition preferably ranges from 1% to 10% by weight, more preferably from 1 to 5% by weight, with respect to the total weight. Said modified polypropylene is a homopolymer or copolymer with various degrees of crystallinity, and can be prepared, according to known methods, by mixing in the solid state the polypropylene and maleic anhydride, isophorone bismaleamic acid or acrylic acid, preferably in the presence of radical initiators, such as organic peroxides. As an alternative, one can add to the crosslinked polyolefin composition some concentrates of

the polypropylene with the modifying agent (i.e., maleic anhydride, isophorone bismaleamic acid or acrylic acid) and the radical initiator, thus causing the modification in situ during the mixing step. In any case, said mixing step is carried out by extrusion in the molten state using the methods described above.

In order to proceed with the coating of the pipes, the polyolefin composition obtained in such a manner is converted into films, tapes, or strips preferably from 300 to 1000 μm thick. At the time of the conversion of said crosslinked polyolefin composition into films, tapes or strips, one can apply tension to the hot product which has already solidified (ca. 100-130 °C) thus obtaining a thermoshrinkable film, tape or strip (thermoshrinkability preferably ranging from 5 to 20%).

Thermoshrinkability of the materials means that the surface of said materials is reduced by the effect of heat, and it is determined by placing a specimen of the material, with known dimensions, into an oven at 120-130 °C for ten minutes, and measuring said specimen at the end of the treatment. If we call the initial surface I, and the surface after treatment I', the thermoshrinkability percentage is obtained with the following formula:

$$[(I-I')/I] \times 100$$

In cases where the pipes are coated by way of hot-melt adhesives, said adhesives are preferably selected from polyolefin compositions comprising from 90 to 99% by weight of one or more propylene random copolymers having a melt temperature (determined by DSC, i.e., Differential Scanning Calorimetry) ranging from 130 °C and 145 °C, and from 1 to 10% by weight of the above mentioned polypropylene modified with maleic anhydride, isophorone bismaleamic acid or acrylic acid. In particular, the above mentioned random copolymers are selected from:

- propylene/ethylene copolymers having a polymerized ethylene content of from 1 to 10% by weight;
- copolymers of propylene and one or more C₄-C₈ α -olefins containing from 2 to 15% by weight of the α -olefin(s);
- copolymers of propylene with ethylene and one or more C₄-C₈ α -olefins, containing from 1.5 to 5% by weight of ethylene, and from 2.5 to 10% by weight of the above mentioned C₄-C₈ α -olefins;
- mixtures of (weight percentages):
 - 1) 30-65%, preferably 35-65%, more preferably 45-65%, of a copolymer of propylene with a C₄-C₈ α -olefin, containing from 98 to 80%, preferably from 95 to 85%, of propylene;
 - 2) 35-70%, preferably 35-65%, more preferably 35-55%, of a propylene/ethylene copolymer with optionally from 2 to 10%, preferably from 3 to 6%, of a C₄-C₈ α -olefin, where the ethylene content ranges from 2 to 10%, preferably from 7 to 9%, when the C₄-C₈ α -olefin is not present, and from 0.5 to 5%, preferably from 1 to 3%, when the C₄-C₈ α -olefin is present.

In the above mentioned random copolymers the C₄-C₈ α -olefin are preferably selected from those listed for the crosslinked polyolefin compositions described above. The mixtures of random copolymers (1) and (2), which are particularly preferred are described in published European patent application 483523.

Generally, both the polyolefin compositions comprising fractions (A), (B), and (C), which are eventually crosslinked, and the random propylene copolymers contained in the above mentioned hot-melt adhesives are prepared by one or more polymerization steps using highly stereospecific Ziegler-Natta catalysts. In particular, one may use catalysts comprising the product of the reaction of (1) a solid component containing a titanium compound and an internal electron-donor compound supported on magnesium chloride, (2) an Al-alkyl compound and (3) an external electron-donor compound.

The preferred titanium compound is the TiCl₄, and preferably the internal donor is selected from the di- and polyethers and alkyl, cycloalkyl, or aryl phthalates, such as for example diisobutyl, di-n-butyl and di-n-octyl phthalate.

The external donor is preferably selected from the silicon compounds containing one or more -OR groups, where R is a hydrocarbon radical. Specific examples are: diphenyldimethoxysilane, dicyclohexyldimethoxysilane, methyl-tert-butyldimethoxysilane, diisopropyldimethoxysilane and phenyltriethoxysilane.

In cases where one uses the hot-melt adhesive described above, the crosslinked polyolefin composition which makes up the coating material is used as is, without adding the polypropylene modified with maleic anhydride, isophorone bismaleamic acid or acrylic acid. Said crosslinked polyolefin composition is used in the form of films, tapes or strips having the thickness mentioned above. Also the hot-melt adhesive can be used in the coating process in the form of films, tapes or strips with a thickness preferably ranging from 50 to 800 μm . As an alternative, an equivalent thickness of hot-melt adhesive can be coextruded on the side of the crosslinked polyolefin composition film, tape or strip which is put in contact with the pipe to be coated, or can be obtained by applying a layer of powder of said adhesive.

The outside surface of the pipe in question which must be coated with the above mentioned materials can be subjected to a cleaning pretreatment, for example with a brush or by sanding.

At any rate, it is best if before applying the adhesives and coating materials, one applies to the outside surface of the pipe one or more primers (such as epoxy resins, silanes, or cromates, for example). It is also preferable to heat the area to be coated before the adhesive and coating material are applied. For this purpose one can simply use the gas torches mentioned above. As a way of example, the temperature of the exposed metal during the above mentioned heating step is brought to about 80-200 °C. The coating is then easily obtained by wrapping the pipes with the above mentioned crosslinked polyolefin composition films, tapes or strips, optionally interposing hot-melt adhesives, and heating the layer of polyolefin material obtained in this manner. The temperature during this heating step may reach 150 ° to 220 °C, for example. In order to obtain the best adhesion of the final coating, the crosslinked polyolefin composition films, tapes, or strips are kept under tension during the above mentioned heating step, thanks to their thermoshrinkable capacity which allows a good elastic recovery.

As previously stated, due to the high viscoelasticity of the crosslinked polyolefin compositions in the molten state, one can maintain the above mentioned tensions throughout the heating step without causing nonhomogeneity and/or tearing in the final coating. One can also use gas torches as a source of heat without running into the above mentioned problems. Obviously, although not necessary, in every heating step one can also use more sophisticated devices such as radiant panels, electric heating coils, induction ovens, or infrared lamps.

The following examples are given in order to illustrate and not limit the present invention.

Example 1

The outside surface of a section of steel pipe 2 meters long, 6 mm thick, and with a diameter of 273 mm, is sanded to a degree of finish equal to Sa 2 1/2 (method SIS 055900). Said section of pipe is then heated to 180 ° - 200 °C with a gas torch, and a layer of about 100 µm of a single-component epoxy primer in powder form is applied (Eurokote 714-32 powder marketed by Biotumes Spéciaux). Subsequently the pipe is wrapped with a tape consisting of a hot-melt adhesive film with a thickness of 400 µm. Said adhesive, based on propylene random copolymers, melts at 141 °C (DSC analysis) and has the following composition (weight percentages):

- 48.25% propylene/ethylene copolymer comprising 4% of ethylene;
- 48.25% propylene/1-butene copolymer comprising 15% of 1-butene;
- 3.5% of polypropylene homopolymer modified with 1.6% maleic anhydride.

The section of pipe is then wrapped with a tape consisting of a 600 µm thick film made of a crosslinked polyolefin composition. Said composition has been prepared starting with a uncrosslinked heterophasic composition consisting of (weight percentages):

- A) 40% of homopolymer of propylene having an isotactic index of 97.5%;
- B) 15% at a polymer fraction containing ethylene, insoluble in xylene at ambient temperature;
- C) 45% of an amorphous ethylene/propylene copolymer fraction containing 50% of ethylene, and soluble in xylene at ambient temperature.

The above mentioned heterophasic composition is extruded at 190 °C with 2 parts by weight of vinyltriethoxysilane and 0.1 parts by weight of dicumylperoxide per 100 parts by weight of heterophasic composition. Using the same extrusion method, the polymer product thus obtained has been further mixed with 0.2 parts by weight of tin dibutylaurate per 100 parts by weight of polymer product, and the total mixture has been converted into the above mentioned film using a flat extrusion die. The film was then kept in water at 23 °C for 48 hours in order to obtain crosslinking.

The resulting film of the polyolefin composition has hot-set values of 70-80% at 200 °C, and 0-8% at 23 °C, calculated by way of CEI 20-31, and a thermoshrinkability of 15%. During the entire coating step, the temperature of the section of the pipe is maintained at 180 °-200 °C using a gas torch as the heating device. The film is wrapped while being maintained under tension, which is about 1N/centimeter of film width, for example.

In Table 1 are shown the results of the adhesion test at 100 °C, impact and cathode peeling resistance at 23 °C.

Example 2

The procedure is the same as for Example 1, but in this case the coating is done using a single ribbon shaped film obtained by coextruding the hot-melt adhesive and crosslinked polyolefin composition film of

Example 1. In this case the crosslinking is obtained by simply exposing the coextruded film to air humidity.

The hot-melt layer of the coextruded film is 50 μm thick, while the cross-linked polyolefin composition layer is 450 μm thick. The coextruded film has a thermoshrinkability of 15%.

The adhesion, impact and cathodic peeling resistance of the coextruded film are shown in Table 1. As one can see from the table, said properties are the same as those obtained for Example 1.

The same results, coupled with the advantage of a more homogeneous coating when the latter is applied to long sections of pipes, are obtained by wrapping the pipes with a tape made up of a hot-melt adhesive film described in Example 1 and 500 μm thick, and then with a tape made up of the coextruded film described above, using the same application techniques as for Example 1.

Example 3

The procedure is as for Example 1, but the tape used for the coating is made up of a 800 μm thick film obtained in the following manner.

The same uncrosslinked heterophasic composition as used in Example 1 is crosslinked in the same way as in Example 1, but during extrusion, together with the vinyltriethoxysilane, 3.5 parts by weight of a concentrate is added having the following composition (weight percentages):

- 94% of the same uncrosslinked heterophasic composition of Example 1;
- 5% of maleic anhydride;
- 1% of 2,5-dimethyl-2,5-di(tert-butylperoxy)hexane.

The product thus obtained is then crosslinked with water and converted into film by using the same procedure described in Example 1.

In Table 1 are shown the results of the adhesion test, impact and cathode peeling resistance.

Comparative example 1

The process is the same as for Example 1, with the difference that the coating material used is a tape made of the uncrosslinked heterophasic composition described in Example 1, which is neither extruded with vinyltriethoxysilane nor subsequently crosslinked. The coating obtained has large tears and splits in the polymer layer.

TABLE 1

TEST	METHOD	CONDITIONS	UNIT	EX. 1	EX. 2	EX. 3
Adhesion at 23°C	DIN 30670	90° angle 10 mm/min 5 cm tape	N/mm	8-12	8-12	8-12
Adhesion at 100°C	idem	idem	N/mm	2-4	2-4	2-4
Impact resistance at 23°C	DIN 30670	25 mm plunger rigid impact	Nmm/mm	10-12	10-12	10-12
Cathode peeling at 23°C	BRITISH GAS PS-CW6	duration: 28 days tension: 1.5V solution: 3% NaCl	mm advance	5-10	5-10	5-10

Claims

1. A process for coating metal pipes wherein the coating material is a polyolefin composition comprising:
 - A) 10-60 parts by weight of homopolymer polypropylene with an isotactic index higher than 90, or a crystalline copolymer of propylene with ethylene and/or with a $\text{CH}_2 = \text{CHR}$ α -olefin, where R is an

alkyl radical with 2-6 carbon atoms, containing over 85% by weight of propylene and having an isotactic index higher than 85%, or mixtures thereof;

B) 10-40 parts by weight of a polymer fraction containing ethylene, insoluble in xylene at ambient temperature;

C) 30-60 parts by weight of an amorphous ethylene-propylene copolymer fraction optionally containing minor proportions of a diene, soluble in xylene at ambient temperature, and containing 40-70% by weight of ethylene,

said polyolefin composition being crosslinked by grafting the polyolefin backbone with an alkenyl-substituted alkoxyisilane and then by contacting with water until one obtains hot-set values, according to regulation CEI 20-31, lower than 175% at 200 °C, and lower than 15% at 23 °C.

2. The process of claim 1, wherein the polyolefin composition used is crosslinked by grafting an alkenyl-substituted alkoxyisilane selected from the group consisting of vinyltriethoxysilane, allyltriethoxysilane and divinyltrimethoxysilane.

3. The process of claim 1, wherein the crosslinked polyolefin composition is mixed with a quantity ranging from 1 to 10% by weight, with respect to the total weight of the composition, of a polypropylene modified with from 1 to 10% by weight of maleic anhydride, isophorone bismaleamic acid or acrylic acid, and is applied to the pipe in the form of film, tape or strips.

4. The process of claim 1, wherein the crosslinked polyolefin composition is applied to a hot melt adhesive coated metal pipe in the form of film, tape or strips, wherein the hot-melt adhesive used to coat the metal pipe is comprised of a polyolefin composition comprising from 90 to 99% by weight of at least one propylene random copolymer having a melt temperature ranging from 130 to 145 °C, and from 1 to 10% by weight of polypropylene modified with from 1% to 10% by weight of maleic anhydride, isophorone bismaleamic acid or acrylic acid.

5. A polyolefin composition comprising:

A) 10-60 parts by weight of homopolymer polypropylene with an isotactic index higher than 90, or a crystalline copolymer of propylene with ethylene and/or with a $\text{CH}_2 = \text{CHR}$ α -olefin, wherein R is an alkyl radical with 2-6 carbon atoms, containing over 85% by weight of propylene and having an isotactic index higher than 85%;

B) 10-40 parts by weight of a polymer fraction containing ethylene, insoluble in xylene at ambient temperature;

C) 30-60 parts by weight of an amorphous ethylene-propylene copolymer fraction containing 40-70% by weight of ethylene, optionally containing minor proportions of a diene, and soluble in xylene at ambient temperature;

said polyolefin composition being crosslinked by grafting onto the polyolefin backbone an alkenyl-substituted alkoxyisilane and then by contacting with water until one obtains hot-set values, according to method CEI 20-31, lower than 175% at 200 °C, and lower than 15% at 23 °C.

6. The polyolefin composition of claim 5, wherein the alkenyl-substituted alkoxyisilane is selected from the group consisting of vinyltriethoxysilane, allyltriethoxysilane and divinyltriethoxysilane.

7. A film, tape or strip for coating pipes, comprising the polyolefin composition of claim 5, and having a thickness from 300 to 1000 μm .

8. The film, tape or strip of claim 7, wherein the polyolefin composition is mixed with from 1 to 10% by weight, with respect to the total weight of the composition, of a polypropylene modified with from 1 to 10% by weight of maleic anhydride, isophorone bismaleamic acid or acrylic acid.

9. A film, tape or strip for coating pipes, comprising: a layer, from 300 to 1000 μm thick, of the polyolefin composition comprising a polyolefin composition comprising:

A) 10-60 parts by weight of homopolymer polypropylene with an isotactic index higher than 90, or a crystalline copolymer of propylene with ethylene and/or with a $\text{CH}_2 = \text{CHR}$ α -olefin, wherein R is an alkyl radical with 2-6 carbon atoms, containing over 85% by weight of propylene and having an isotactic index higher than 85%;

B) 10-40 parts by weight of a polymer fraction containing ethylene, insoluble in xylene at ambient temperature;

C) 30-60 parts by weight of an amorphous ethylene-propylene copolymer fraction containing 40-70% by weight of ethylene, optionally containing minor proportions of a diene, and soluble in xylene at ambient temperature;

said polyolefin composition being crosslinked by grafting onto the polyolefin backbone an alkenyl-substituted alkoxysilane and then by contacting with water until one obtains hot-set values, according to method CEI 20-31, lower than 175% at 200 °C, and lower than 15% at 23 °C, and

a layer, from 50 to 800 μm thick, of a hot-melt adhesive which is comprised of a polyolefin composition comprising from 90 to 99% by weight of at least one propylene random copolymer having a melt temperature ranging from 130 to 145 °C, and from 1 to 10% by weight of polypropylene modified with from 1% to 10% by weight of maleic anhydride, isophorone bismaleamic acid or acrylic acid.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 94 10 5321

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.5)
Y	EP-A-0 124 247 (UBE) * page 3, line 32 - page 5, line 9 * * page 8, line 3 - line 10 * * page 9, line 11 - line 24 * ---	1-10	C08L51/06 C09D151/06 C08K5/54
D,Y	EP-A-0 400 333 (HIMONT) * page 3, line 4 - line 17 * ---	1-10	
X	DATABASE WPI Derwent Publications Ltd., London, GB; AN 81-40739D & JP-A-5 609 386 (SHOWA ELEC WIRE) 15 April 1981 * abstract * ---	1,2	
A	WO-A-903 850 (DOW BENELUX) * page 5, line 30 - page 6, line 20 * ---	3,4,8,9	
A	EP-A-0 004 034 (FURUKAWA ELECTRIC) * page 6, line 3 - line 19 * * page 8, line 7 - line 32 * ---	1-10	
A	EP-A-0 412 518 (UNION CARBIDE) * page 3, line 37 - line 45 * * page 4, line 4 - line 15 * ---	1-10	TECHNICAL FIELDS SEARCHED (Int.Cl.5) C08L C09D C08K
A	EP-A-0 503 361 (BASF) * page 4, line 54 - page 5, line 28 * * page 5, line 42 - line 45 * -----	1-10	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 8 July 1994	Examiner Schmidt, H
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 1503 03.92 (P04C01)